

FLAMMADUR® A 365

Two-component casting resin

Description

FLAMMADUR® A 365 is a black two-component polyurethane casting resin that forms an insulating layer. It is suitable for the production of cable penetrations, elastic panels and moulded parts for preventive fire protection.

Areas of Application

- Cable management
- Rolling stock
- Ships & offshore
- On request



Delivery and Packaging

FLAMMADUR® A 365				
Packaging	tin	drum	sep. hardener	
Size	1 kg	250 kg	5 kg	25 kg
Article number				
	4146389	4146289	4146348	4145953

Please contact us for further information:

☎ +49 4105-40 90-14

✉ transportation@svt.de



FLAMMADUR® A 365

Technical Data

	FLAMMADUR® A 365 (resin)	FLAMMADUR® A 365 (hardener)
Mixing ratio (parts by weight)	100	12
Mixing ratio (parts by volume)	7.0	1.0
Viscosity	approx. 25 000 mPa·s	approx. 40 mPa·s
Viscosity of the mixture	~ 9000 mPa·s	
Density	1.46 kg/l	1.22 kg/l
Mixing density	1.45 kg/l	
Pot life Bookfield RVT, +23 °C	4–30 min (adjustable)	
Curing time	3–24 hrs	
Flashpoint	> 200 °C	> 200 °C
Processing information	<ul style="list-style-type: none"> The surfaces being cast must be dry and clean. Tools for the production of moulded parts must be provided with a suitable release agent. Processing is preferably carried out in a casting process with two-component dosing systems or by manual casting. FLAMMADUR® A 365 is insensitive to moisture and largely resistant to common technical oils and weak/diluted acids and alkalis. 	
Processing (min. +5 °C / < 90 % relative humidity)	<p>With manual casting, the processing time at +23 °C between 4–30 minutes, the curing time is 3–24 hours.</p> <p>The pot life and curing times are adjustable and depend on the temperature</p>	
Storage	Max. 6 months in the original unopened container. Protect from frost.	
Safety instructions	<p>FLAMMADUR® A 365 is fibre and solvent free and not subject to any dangerous goods class.</p> <p>Consult the safety data sheet for additional instructions.</p>	

Moulding material

Shore hardness (DIN 53505)	88–92 Shore A; 32–35 Shore D
Expansion pressure (300 °C) method A, sample thickness 5 mm, Ø 70 mm (DIBt guidelines, 1996)	0.6–1.2 N/mm²
Expansion (450 °C)	17 to 26 times
Application temperature range	-50 °C to +80 °C

Classification	<p>The product meets the requirements R1 for hazard levels HL1–HL3 as per DIN EN 45545-2 (02/2016) DMT PB Nr. 8116069434-20</p> <p>The product meets the requirements R17 for hazard levels HL2 DIN EN 45545-2 (02/2016) DMT PB Nr. 8116069434-20</p> <p>The product meets the requirements according to DIN 5510:Teil 2 (05/2009) Exova PB-Nr. 2016-2003</p>
----------------	---